



# DURAPURE DESIGN FLOORS



## LAYER THICKNESS

2 to 2,5 mm.

## CURE THOUGH

Durapure is walkable 24 hours after the installation. The complete chemical and mechanical properties will be achieved after 7 days of curing at a minimum temperature of 15°C.

## MAINTENANCE

Regular removal of dust and if necessary wet cleaning with a neutral cleaning agent. For further instructions see the maintenance instruction guide.

## INSTALLATION

The concrete or screed subfloor has to be primed and levelled with a self levelling smoothing compound to obtain a flat and levelled surface. Uneven surfaces have to be leveled by e.g. diamond grinding prior to the levelling compound. All dust and loose parts have to be fully removed from all surfaces before the product is applied, preferably using a brush and/or industrial vacuum cleaner. Prior to the installation of the Durapure a suitable primer needs to be applied. During the installation the room temperature needs to be at least 62 °F (15,5°C). The floor temperature need to be at least 59 °F (15°C) and minimum 3 °F (3 °C) above the dew point.

## COMPOSITION

Durapure is a flexible uni colored resilient floor covering. The Durapure has tough-elastic properties and is Red List Free.

## APPLICATION

Durapure is a tough, flexible seamless comfortable floor covering. Durapure can be used as a seamless design floor covering in the education sector, medical sector, offices, museums, but is also suitable for domestic surfaces. In short Durapure is a perfect solution for floors where the owners and users have a high demand on comfort, wear and impact resistance and hygiene. Durapure is a seamless solution from wall to wall. Durapure is available in different versions.

## APPEARANCE

Durapure has an unicolor appearance with a smooth level surface. can also be applied in a colormix by blending two colors creating a marbling effect. Durapure can be made in any color requested.

## CLASSIFICATION

**CLASS 23 DOMESTIC HEAVY**  
Minimum thickness 2 mm

**CLASS 34 COMMERCIAL VERY HEAVY**  
Minimum thickness 2 mm

**CLASS 23 DOMESTIC HEAVY**  
Minimum thickness 2 mm

## TECHNICAL DATA

**RESISTANCE TO INDENTATION**  
EN ISO 24343-1 • 0.03 mm • ASTM F-1914 • 0.001inch / 750 PSI

**EFFECT OF A FURNITURE LEG**  
EN 424 • No damage • Static Load Limit: exceeds 1000 PSI when tested in accordance ASTM F-970-00

**ABRASION RESISTANCE**  
ASTM D4060 -14 • CS17 • Wheels/10N/1500 cycles • 55 mg

**ELECTRICAL BEHAVIOR**  
EN 1815 • < 2 kV

**LIGHTFASTNESS**  
EN ISO 105-B02 • 7 - 8 • ASTM F-1515 • 7 - 8 (1-Severe change, 8-No change)

**FLEXIBILITY**  
EN 435 • 20 mm, no cracking • ASTM F-137-08 • 0.79 inch, no cracking

**RESISTANCE TO CHEMICALS**  
EN ISO 26987 • No changes • Passes in accordance with ASTM F-925 • No change

**STAINING RESISTANCE**  
EN 423 • Category 1+2: level 5, Category 3: level 4/5

**CIGARETTE RESISTANCE**  
EN 1399 • Proc A (stubbed out) ≥ level 4 • Proc B (burning) ≥ level 3

**THERMAL CONDUCTIVITY**  
EN ISO 12524 • 0.15 W/m.K, suitable for underfloor heating • ASTM C-518-17 • 0.15 W/m.K

**THICKNESS SWELLING**  
EN 13329 • < 0,8%

**SUITABILITY FOR USE IN INCIDENTAL HUMID CONDITIONS**  
EN 426 • Suitable

**CE NUMBER**  
15 • DoP08COR0017 • EN 13813:2002

**DURAPURE DESIGN FLOORS**  
Contains recycled content

**REACTION TO FIRE** EN 13501-1 • Bfl-S1 • Class 1 when tested in accordance with ASTM E-648 Critical Radiant Flux  
• Meets 450 or less, when tested in accordance with ASTM 662/ NFPA 258 Smoke Density

**CASTOR CHAIR CONTINUOUS USE** EN 425 • 25.000 • Slight change in appearance • no delamination • ASTM D-6962 • 25.000 • slight change • no delamination

**SLIP RESISTANCE** DIN 51130 • R9 standard / R11 upon request • EN 13893 • DS: ≥ 0.30 • Meets or exceeds the industry recommendation of >0.5 for flat surfaces when tested in accordance with ASTM D-2047



WANT TO  
KNOW MORE  
ABOUT THE  
PRODUCT?  
CLICK HERE!

