SPECIFICATION DOCUMENT AND SAFETY DATA INFORMATION




DURAPURE DESIGN FLOORS

Declare.









COMPOSITION

Durapure is a flexible uni colored resilient floor covering. The Durapure has tough-elastic properties and is Red List Free.

APPLICATION

Durapure is a tough, flexible seamless comfortable floor covering. Durapure can be used as a seamless design floor covering in the education sector, medical sector, offices, museums, but is also suitable for domestic surfaces. In short Durapure is a perfect solution for floors where the owners and users have a high demand on comfort, wear and impact resistance and hygiene. Durapure is a seamless solution from wall to wall. Durapure is available in different versions.

APPEARANCE

Durapure has an unicolor appearance with a smooth level surface. can also be applied in a colormix by blending two colors creating a marbling effect. Durapure can be made in any color requested.

LAYER THICKNESS

2 to 2,5 mm.

CURE THOUGH

Durapure is walkable 24 hours after the installation. The complete chemical and mechanical properties will be achieved after 7 days of curing at a minimum temperature of 15°C.

MAINTENANCE

Regular removal of dust and if necessary wet cleaning with a neutral cleaning agent. For further instructions see the maintenance instruction

INSTALLATION

The concrete or screed subfloor has to be primed and levelled with a self levelling smoothing compound to obtain a flat and levelled surface. Uneven surfaces have to be leveled by e.g. diamond grinding prior to the levelling compound. All dust and loose parts have to be fully removed from all surfaces before the product is applied, preferably using a brush and/or industrial vacuum cleaner. Prior to the installation of the Durapure a suitable primer needs to be applied. During the installation the room temperature needs to be at least 62 °F (15,5°C). The floor temperature need to be at least 59 °F (15°C) and minimum 3 °F (3 °C) above the dew point.

























SPECIFICATION DOCUMENT AND SAFETY DATA INFORMATION

DURAPURE DESIGN FLOORS



CLASSIFICATION



CLASS 23 DOMESTIC HEAVY
Minimum thickness 2 mm



CLASS 34 COMMERCIAL VERY HEAVY



CLASS 43 INDUSTRIAL HEAVY
Minimum thickness 2 mm

TECHNICAL DATA



RESISTANCE TO INDENTATION EN ISO 24343-1 • 0.03 mm • ASTM F-1914 • 0.001inch / 750 PSI



EFFECT OF A FURNITURE LEG

EN 424 • No damage • Static Load Limit: exceeds 1000 PSI when tested in accordances ASTM F-970-00



ABRASION RESISTANCE
ASTM D4060 -14 • CS17 • Wheels/10N/1500 cycles • 55 mg



ELECTRICAL BEHAVIOR EN 1815 • < 2 kV



LIGHTFASTNESS

EN ISO 105-B02 • 7 - 8 • ASTM F-1515 • 7 - 8 (1-Severe change, 8-No change)



EN 435 • 20 mm, no cracking • ASTM F-137-08 • 0.79 inch, no cracking



RESISTANCE TO CHEMICALS

EN ISO 26987 • No changes • Passes in accordance with ASTM F-925 • No change



STAINING RESISTANCE EN 423 • Category 1+2: level 5, Category 3: level 4/5



CIGARETTE RESISTANCE

EN 1399 • Proc A(stubbed out) ≥ level 4 • Proc B(burning) ≥ level 3



THERMAL CONDUCTIVITY
EN ISO 12524 • 0.15 W/m.K, suitable for underfloor heating • ASTM C-518-17 • 0.15 W/m.K



ACCOUSTICAL IMPACT NOISE REDUCTION

EN ISO 12524 • ASTM E-2179 03 • A Lw = 8dB Corques • 15dB Corques Comfort



THICKNESS SWELLING EN 13329 • < 0,8%



WATER TIGHTNESS





SUITABILITY FOR USE IN INCIDENTAL HUMID CONDITIONS



C € CE NUMBER15 • Do PO8CORQ017 • EN 13813:2002



DURAPURE DESIGN FLOOR Contains recycled content



REACTION TO FIRE EN 13501-1 - Bfl-S1 - Class 1 when tested in accordance with ASTM E-648 Critical Radiant Flux - Meets 450 or less, when tested in accordance with ASTM 662/ NFPA 258 Smoke Density





 $\textbf{CASTOR CHAIR CONTINUOUS USE} \ EN \ 425 \cdot 25.000 \cdot \text{Slight change in appearance} \cdot \text{no delamination} \cdot \text{ASTM D-6962} \cdot 25.000 \cdot \text{slight change} \cdot \text{no delamination}$



SLIP RESISTANCE DIN 51130 • R9 standard / R11 upon request • EN 13893 • DS: \geq 0,30 • Meets or exceeds the industry recommendation of >0.5 for flat surfaces when tested in accordance with ASTM D-2047

* However the ASTM F-2034 and teh ASTM F-2195 are designed for sheeted or tiled linoleum Durapure Design Floor fulfills or exceeds all technical requirements mentioned in these ASTM normatives.



WANT TO KNOW MORF **ABOUT THE** PRODUCT? CLICK HERE!





Duracryl International BV

Elandstraat 91 2901 BK Capelle a/d IJssel The Netherlands +31 10 458 85 52 info@duracryl.com



Duracryl International GmbH Maybachstrasse 6 D 71397 Nellmersbach +49 7195 59296-0 vertrieb@duracryl.com





United States of America +1 (469) 243 4107 sales@duracryl.com











